

PRODUCT SPECIFICATIONS : DOUBLE A 100 gsm

Parameter	Methods	Values
Basis weight (g/m ²)	ISO 536	100
Thickness (µm)	ISO 534	132
Whiteness CIE	ISO 11475	165
D65 Brightness (%)	ISO 2470	111
Opacity (%)	ISO 2471	> 97
Moisture content (%)	ISO 287	4.2
Bendtsen roughness (ml/min)	ISO 8791-2	90
Kodak Stiffness MD (mN.m)	ISO 5629	0.70
Kodak Stiffness CD (mN.m)		0.28

ve
MPROMISE.

These values are indicative only.
Valid from : September 2014