

PRODUCT SPECIFICATIONS : Double A 70

Parameter	Methods	Values
Basis weight (g/m ²)	ISO 536	70
Thickness (µm)	ISO 534	100
Whiteness CIE	ISO 11475	165
D65 Brightness (%)	ISO 2470	111
Opacity (%)	ISO 2471	> 93
Moisture content (%)	ISO 287	4
Bendtsen roughness (ml/min)	ISO 8791-2	90
Kodak Stiffness MD (mN.m)	ISO 5629	> 0.35
Kodak Stiffness CD (mN.m)		> 0.14
Bending Stiffness MD (mN)	ISO 2493	> 90
Bending Stiffness CD (mN)		> 40

These values are indicative only.
Valid from : July 2014