

## PRODUCT SPECIFICATIONS : DOUBLE A 90 gsm

Parameter	Methods	Values
Basis weight (g/m <sup>2</sup> )	ISO 536	90
Thickness (µm)	ISO 534	118
Whiteness CIE	ISO 11475	165
D65 Brightness (%)	ISO 2470	111
Opacity (%)	ISO 2471	> 96
Moisture content (%)	ISO 287	4.2
Bendtsen roughness (ml/min)	ISO 8791-2	90
Kodak Stiffness MD (mN.m)	ISO 5629	0.50
Kodak Stiffness CD (mN.m)		0.20

ve  
MPROMISE.

These values are indicative only.  
Valid from : September 2014